



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166
(571) 300-7050 • www.capitaltesting.org

TEST REPORT

Test Method: CAN/ULC-S102.2:2018-REV1, Standard Method of Test for Surface Burning Characteristics of Flooring, Floor Coverings, and Miscellaneous Materials and Assemblies

Rendered To: Octo Prints and Lighting
16637 Fishhawk Blvd., Suite 104
Lithia, FL 33547

Product Description: Fabric Fluorescent / LED Light Cover

Report Number: T-18365

Original Issue Date: 06/09/2026

Test Date: 05/26/2026 – 05/27/2026

Pages: 9



TL-224

The observations and test results in this report are relevant only to the sample(s) tested. Capital Testing and Certification Services (herein referred to as Capital Testing) does not verify information that is provided by the client. This test report in no way constitutes or implies product certification, approval or endorsement by Capital Testing. Capital Testing assumes no liability to any party, other than to the Client in accordance with the terms and conditions agreement, for any loss, expense or damage occasioned by the use of this report. This report, the Capital Testing name or any of its marks, shall not be used for the sale or advertisement of the tested material. This report shall not be reproduced, except in full, or modified in any way.



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166

(571) 300-7050 • www.capitaltesting.org

I. SCOPE

This test report contains the results from a specimen tested in accordance with CAN/ULC-S102.2, *Standard Method of Test for Surface Burning Characteristics of Flooring, Floor Coverings, and Miscellaneous Materials and Assemblies*. The results of CAN/ULC-S102.2 testing are commonly used by building code officials and regulatory agencies to determine whether interior finish materials are suitable for their intended application.

II. TEST SPECIMENS

Test specimens should be representative of the material which the test is intended to examine. All test specimens should be approximately 10mm narrower than the interior width of the tunnel and 7315 ± 15 mm in length. The maximum allowable thickness is 65mm. The test specimen can be provided in a continuous, unbroken length or multiple sections that will be butted together. Prior to testing, the specimens are conditioned to a constant mass in an environment that is held at 23 ± 3 °C (73.4 ± 5.4 °F) and $50 \pm 5\%$ relative humidity.

TEST SPECIMEN INFORMATION	
Product Description	Fabric Fluorescent / LED Light Cover; Nominal Thickness: 8 mil Polyester Fabric. *
Samples Selected By	Client
Date Received	03/31/2026
Conditioning Time (days)	55 (Burn 1), 56 (Burn 2)
Specimen Size (in.)	17-1/2 x 288
Continuous / Sectioned	Sectioned
Number of Sections	Three 17-1/2" x 96" specimens
Avg. Total Weight (lbs.)	62.5
Average Thickness (in.)	0.002
Color	White*
Exposed Surface	Face Side* (Coated side)
Mounting Method	Sample material was fastened onto 1/4" cement board using 1/4" T50 staples. Staples were spaced every 6" around the perimeter of the specimen.

* Information provided by the Client



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166
(571) 300-7050 • www.capitaltesting.org

III. PROCEDURE

The tunnel is preheated to 85 ± 5 °C (185 ± 9 °F) as measured by a thermocouple embedded in the backwall of the furnace at 7090 mm (23.3 ft) from the centerline of the burner. The tunnel is then cooled to 40 ± 3 °C (104 ± 5.4 °F) as measured by a thermocouple embedded in the backwall of the furnace at 4000 mm (13.1 ft) downstream of the centerline of the burner.

After the tunnel has cooled to the required temperature range, the tunnel lid is lifted, and the test specimen is placed on the ledges of the tunnel. The specimen is mounted in a ceiling orientation with the side that will be exposed to the flame facing downward. A 6 mm (0.25 in.) fiber-cement board is placed on the backside of the specimens to protect the tunnel lid during testing.

Once the sample has been loaded into the test chamber, the lid is lowered, and a 1.2 ± 0.025 m/s (236.2 ± 4.9 ft/min) airflow is established. The test specimen is preheated for approximately 2 minutes prior to applying the 90-kW burner. The burner is positioned at the front end of the tunnel. It has two ports that point downward at a 45° angle toward the face of the specimen. An air ramp is placed at the front end of the specimen to reduce air eddies and to prevent low density material from being blown away from the burner.

After the 2-minute preheat, the burner is ignited, and it remains on for the duration of the 10-minute test. The flame is tracked by an observer, referred to as the Reader, as it progresses down the length of the tunnel. Smoke density is measured with the use of the photometer system on the exhaust duct. Temperature data is recorded throughout the test by a thermocouple probe that is 7000 mm (23 ft) from the centerline of the burner and approximately 25mm (1 in.) below the upper ledges of the tunnel.

IV. CALCULATION OF RESULTS

In CAN/ULC-S102 testing, test results for individual burns are reported as Flame Spread Value (FSV) and Smoke Developed Value (SDV). The average indices, that are derived from a minimum of three individual burns, are reported as Flame Spread Rating (FSR) and Smoke Developed Classification (SDC).

The Flame Spread Value is derived by plotting the flame spread distance versus time. Only progressive flame spread is plotted. The total area (A_T) under the flame spread distance-time plot is determined by ignoring any flame front recession. The calculation of FSV is described below:

$$\text{When } A_T \leq 29.7 \text{ m} \cdot \text{min:} \quad \text{FSI} = 1.85 * A_T$$

$$\text{When } A_T > 29.7 \text{ m} \cdot \text{min:} \quad \text{FSI} = 1640 / (59.4 - A_T)$$

The Smoke Developed Value is derived by plotting the photoelectric cell readings versus time. The area under the curve for the tested material is then divided by the area under the curve for select-grade red oak flooring. The resulting value is then multiplied by 100.

The Flame Spread Rating is determined by averaging a minimum of three individual Flame Spread Values and rounding that average to the nearest multiple of 5. The Smoke Developed Classification is determined by averaging a minimum of three individual Smoke Developed Values and rounding that average to the nearest multiple of 5.



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166
(571) 300-7050 • www.capitaltesting.org

V. DISCUSSION

CAN/ULC-S102.2 Standard Language and Disclaimers

The following language was taken directly from the CAN/ULC-S102.2 standard. It has been included for information purposes.

Smoke Developed Value (SDV) and Flame Spread Value (FSV) are recorded in this test. However, there is not necessarily a relationship between these two measurements. – CAN/ULC-S102.2:2018-REV1, Section 1.4

This method defines the relative surface burning characteristics under specified test conditions. Although the procedure is applicable to materials, products and assemblies used in building construction for development of comparative surface spread of flame data, test results may not reflect the relative surface burning characteristics of tested materials under all building fire conditions. – CAN/ULC-S102.2:2018-REV1, Section 3.1

The “fire hazard” of any material in the light of present knowledge cannot be evaluated on the basis of any one test. A body of tests, each measuring one or more characteristics of a material, product, or assembly, may be needed for full assessment. These assessments are intended as aids to those who have the responsibility for determining acceptable levels of potential hazard. The overall fire hazard of a material as it is to be used can only be determined by an analysis of its behavior under several test conditions in addition to further analysis which includes consideration of building construction, occupancy, location and fire protection features. – CAN/ULC-S102.2:2018-REV1, Section 3.2

VI. TEST RESULTS

FLAME SPREAD RATING (FSR)	SMOKE DEVELOPED CLASSIFICATION (SDC)
0	0

Test Start Date	05/26/2026
Test End Date	05/26/2026
Equipment Operator	Chris Kaiser
Flame Spread Reader	Tony Norris

	Burn #1	Burn #2	Burn #3
Ignition Time (s)	33	293	248
Flame Spread Value (FSV)	0.0	0.0	0.0
Smoke Developed Value (SDV)	0.3	2.4	-0.2
Maximum Temperature (°C)	324.7	331.6	326.6
Maximum Temperature (°F)	616.4	628.8	619.9
Time to Maximum Temperature (min)	10.00	9.83	9.17
Maximum Flame Spread Distance (m)	0.0	0.0	0.0
Maximum Flame Spread Distance (ft)	0.0	0.0	0.0
Time to Maximum FS Distance (min)	0.0	0.0	0.0



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166
(571) 300-7050 • www.capitaltesting.org

VII. OBSERVATIONS

During Test

Burn 1: Sample material broke apart along the longitudinal centerline of the specimen panel closest to the burner at 89 seconds into the test.

Burn 2: Sample material broke apart along the longitudinal centerline of the specimen panel closest to the burner at 71 seconds into the test.

Burn 3: Sample material broke apart along the longitudinal centerline of the specimen panel closest to the burner at 51 seconds into the test.

After Test

Burn 1: Sample material melted to the cement board backer to 4'. Discoloration of the exposed surface to 7'. Curling of the sample material edges along the perimeter of the assembled specimens to 24'.

Burn 2: Sample material melted to the cement board backer to 5'. Discoloration of the exposed surface to 8'. Curling of the sample material edges along the perimeter of the assembled specimens to 24'.

Burn 3: Sample material melted to the cement board backer to 4'. Discoloration of the exposed surface to 7'. Curling of the sample material edges along the perimeter of the assembled specimens to 24'.

Note: Reported observation distances are relative to the entire length of the test specimen.

VIII. REMARKS

The reported average total weight includes the sample material, cement board backer, and the staples. The reported average thickness only includes the sample material.



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166

(571) 300-7050 • www.capitaltesting.org

IX. GRAPHS AND INDIVIDUAL BURN DATA

Test Method Project # Date

ULC S102.2 T18365 26 May 2026 Time (Test Start) 3:06 PM Test No. 1

Specimen ID

Fabric Fluorescent / LED Light Cover

Specimen Description

8 mil Polyester Fabric


Mounting Procedure

Sample material was mounted onto 1/4" cement board using 1/4" staples spaced 6" apart.


Fuel (CF) 49.23 980 °F Time (min) NaN MAX Temp (°F) 616.4 MAX Temp Time (min) 10.00

FS Area 0.0 MAX FS (m) 0.00 MAX FS Time (min) 0.00 Ign Time (sec) 33


Smoke Area (%A×min) 0.55 Calibration Smoke Area 209.5 Raw SDV 0.3 Raw FSV 0.0



Flame Spread (m)



Smoke (%A)



23 ft Temp (F)

Final FSV 0 Final SDV 0

Test Room Temperature (°F): 74.6

Test Room Humidity (%RH): 52.8

Note: Distances on this page are reported in meters.



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166

(571) 300-7050 • www.capitaltesting.org

Test Method Project # Date Time (Test Start) Test No.

Specimen ID


Specimen Description

Mounting Procedure


Fuel (CF) 980 °F Time (min) MAX Temp (°F) MAX Temp Time (min)

FS Area MAX FS (m) MAX FS Time (min) Ign Time (sec)


Smoke Area (%A×min) Calibration Smoke Area Raw SDV Raw FSV



Flame Spread (m)



Smoke (%A)



23 ft Temp (F)

Final FSV Final SDV

Test Room Temperature (°F): 75.0

Test Room Humidity (%RH): 54.1

Note: Distances on this page are reported in meters.



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166

(571) 300-7050 • www.capitaltesting.org

Test Method Project # Date Time (Test Start) Test No.

Specimen ID


Specimen Description

Mounting Procedure


Fuel (CF) 980 °F Time (min) MAX Temp (°F) MAX Temp Time (min)

FS Area MAX FS (m) MAX FS Time (min) Ign Time (sec)


Smoke Area (%A×min) Calibration Smoke Area Raw SDV Raw FSV



Flame Spread (m)



Smoke (%A)



23 ft Temp (F)

Final FSV Final SDV

Test Room Temperature (°F): 75.3

Test Room Humidity (%RH): 50.6

Note: Distances on this page are reported in meters.



CAPITAL TESTING AND CERTIFICATION SERVICES

42777 Trade West Drive • Sterling, VA 20166
(571) 300-7050 • www.capitaltesting.org

X. AUTHORIZED SIGNATURES

Report Written By:

Chris Kaiser
Lab Technician II

05/27/2026

Date

Reviewed and Approved By:

Chris Palumbo
Sr. Manager of Product Testing

06/09/2026

Date

XI. REVISION HISTORY

Revision Number	Date	Summary
0	06/09/2026	Original Report Issued

XII. ACCREDITATION

Capital Testing and Certification Services is an ISO/IEC 17025 accredited testing laboratory whose scope includes CAN/ULC S102.2. Accrediting Body: International Accreditation Service, Inc. (IAS). Testing Laboratory TL-224.